



Test	Acoustical Tile	Roll Rubber	Versus
ASTM F2772 Classification	Standard Specification for Athletic Performance Properties of Indoor Sports Floor Systems	Standard Specification for Athletic Performance Properties of Indoor Sports Floor Systems	Standard Specification for Athletic Performance Properties of Indoor Sports Floor Systems
D2240 Hardness Durometer	Indentation hardness 65 top and 40 bottom	Top 85 Bottom 80	Indentation hardness 95
ASTM D24047 Slip Resistance Standard Neolite Coefficient of friction on flooring	Dry 0.96 Wet 1.02	Dry 0.84 Wet 0.86	Dry 0.84 Wet 0.86
ASTM 3389 Abrasion Resistance taber 1,000 cycles at 1000 grams	Weight loss 0.42 grams (0.46%)	Weight loss 0.47 grams (0.35%)	Weight loss 0.47 grams (0.35%)
ASTM F 970 Static Load	Residual compression 0.021 inch	0.003 inch residual compression	Residual compression 0.003 inch
F 925 Chemical Resistance	No change in surface attack after 24 hours	No change in surface attack after 24 hours	No change in surface attack after 24 hours
D395 Compression set under force	96.3% recovered	98.55% recovered	98.55% recovered
ASTM D412-06 Tensile Strength	132.3 psi	650.1 psi	130.01 psi
ASTM D412-06 Elongation at break	76.15%	268.53%	268.53%



OTHER APPLICATIONS WHERE HARBINGER™ CAN PROVIDE SOLUTIONS



www.harbingerfloors.com/rubber

1-866-64606519

Sports Flooring that's PVC free, anti-microbial, resilient and durable. Easy maintenance and slip resistance surface with a 5 year warranty.



DIV 9

FLOORING FOR
ICE RINKS
WEIGHT ROOMS
MULTI-PURPOSE